

## **Glazing Options**

Document: D-WE-DSGGO Revision: 1 Issued Date: Dec.18/14 Page: 1 of 1

## **DIAMOND SEA-GLAZE GLAZING OPTIONS**

We offer Tempered and Laminated safety glass in various thicknesses and tints.

Heated glass, sealed units and Lexan MR10 are also available upon request.

Light % refers to the amount of light the glazing will let through. (The lower the number the darker the tint).

TEMPERED GLASS				
NOMINAL THICKNESS	TINT COLOR	LIGHT %	WEIGHT PER SQ.FT (Lbs.)	
1/4"	PINHEAD	OBSCURE	3.20	
1/4"	CLEAR	89%	3.20	
1/4"	GRAY	45%	3.20	
1/4"	GRAYLITE II	9%	3.20	
1/4"	GREEN	73%	3.20	
1/4"	BRONZE	52%	3.20	
3/8"	CLEAR	88%	5.05	
3/8"	GRAY	28%	5.05	
3/8"	BRONZE	38%	5.05	
1/2"	CLEAR	87%	6.40	
1/2"	GRAY	19%	6.40	
1/2"	BRONZE	28%	6.40	
3/4"	CLEAR	84%	6.40	

LAMINATED GLASS				
NOMINAL THICKNESS	TINT COLOR	LIGHT %	WEIGHT PER SQ.FT (Lbs.)	
1/4"	OBSCURE	OBSCURE	2.85	
1/4"	CLEAR	89%	2.85	
1/4"	LIGHT GRAY	44%	2.85	
1/4"	DARK GRAY	28%	2.85	
1/4"	BRONZE	52%	2.85	
1/4"	LIGHT GREEN	73%	2.85	
3/8"	CLEAR	89%	5.05	
3/8"	LIGHT GRAY	44%	5.05	
3/8"	DARK GRAY	28%	5.05	
3/8"	BRONZE	52%	5.05	
1/2"	CLEAR	89%	6.40	
3/4"	CLEAR	77%	10.10	